

Product Datasheet

EurorooF Self-Adhesive Vapour Control Layer

Sheet NO PD013FR

Issued: February 2016

Pages: 1 of 2

Description

EurorooF Self-Adhesive Vapour Control Layer is a polyester reinforced, modified bitumen vapour barrier with an aluminium core, a removable polyethylene film on its underside, and a fine mineral surface.

Use

For use as a vapour control layer in built-up roofing systems, in both new construction and refurbishment projects.

Application

All surfaces to receive membrane must be clean and dry. Prime the substrate with EurorooF Contact Adhesive or EurorooF SA Primer, coverage rate per m² as per the project specification.

Install the EurorooF Self-adhesive Vapour Control Layer with 75mm side and 150mm end laps, by removing the release film and firmly pressure rolling the surface to achieve a continuous bond across the full width of the membrane. Ensure that the membrane is accurately aligned, including overlaps, before removing the release film, and that it does not move as the film is removed.

Side laps are self-adhesive when subject to temperatures of >15° under normal conditions. However, in cold weather or if the lap has become contaminated, hot air equipment should be used to ensure the laps are fully sealed. End laps should be heat welded using hot-air equipment. If left exposed overnight both side and end laps must be heat welded to ensure they are fully sealed.

Substrate/s must be even and free from any irregularities that may compromise the bond. Undertake an adhesion test to establish a full bond can be obtained using the Self-Adhesive membrane to the primed substrate. Please contact Alumasc technical services for further guidance if the bond strength is unsatisfactory.

Storage

Store upright in a clean, dry location, away from heat sources. The product must be stored at between 5°C and 24°C for 24 hours prior to use.

Product Data

Thickness	2.3mm
Width	1.0m
Length	15m
Weight	2.5 kg/m ²
Weight per roll	37.5 kg

Performance Data

Tensile Strength - longitudinal	≥700 N/50mm
Tensile Strength - transverse	≥500 N/50mm
Elongation at break - longitudinal	≥ 35%
Elongation at break - transverse	≥ 35%
Softening point	≥ 100°C
Foil thickness	30 microns
Shelf life	12 months

Product Datasheet

Eurorooft Self-Adhesive Vapour Control Layer

Sheet NO PD013FR

Issued: February 2016

Pages: 2 of 2

Health & Safety

Safety Data Sheets are available upon request, and can also be downloaded directly from www.alumascroofing.co.uk

Technical Support

Technical advice is available from Alumasc Technical Services at:

Tel: +44 (0)1744 648400

Email: roofing@alumasc-exteriors.co.uk

The company pursues a policy of constant product development and information contained in this publication is therefore subject to change without notice. The customer is responsible for ensuring that each product is fit for its intended purpose and that the conditions for use are suitable. All quoted data is nominal and subject to production tolerances.